

Liquid Waterproofer

Description

General purpose single pack black bitumen for waterproofing and weather protecting steelwork and concrete.

Typical properties

Colour Black (shiny when applied, dulls on exposure to sunlight)

Specific Gravity 0.92 ± 0.02 @ 20°C

Flash Point 38°C

Preparation

LIQUID WATERPROOFER should always be applied to surfaces that are clean and free from dust, oil and other surface contaminants. It should not be applied in temperatures below 5°C. repairs to cracks, holes, etc. must be carried out prior to coating.

Uses

LIQUID WATERPROOFER provides an effective waterproof, weatherproof, corrosion resistant protective coating. It is resistant to low concentrations of alkalis and acids and can withstand prolonged oxidation. It is suitable for application to a wide variety of materials including iron and steel, lead, zinc, aluminium, asbestos-cement, concrete, stone and brick. It is mainly used for;

Metal protection – corrugated iron sheets, fire escapes, stairways, ladders, storage tanks, gutters, down pipes, fences, railings, gates, etc. A protective coating for concrete structures, stone, brick, concrete screeds and sand/cement surfaces.

Application

A minimum of two coats of LIQUID WATERPROOFER should be applied by roller, brush or spray, the first coat being allowed to dry before the second is applied

NOTE. LIQUID WATERPROOFER may bleed through any paints subsequently applied over it. Apply a primer recommended by the paint manufacturer before over painting.

Coverage and Drying

On metal and smooth surfaces 10m² per litre, less on rough or porous surfaces.

Drying times will vary depending on weather conditions but is typically 48hours. Heavy application will result in extended drying times.

Cleaning

Tools should be cleaned immediately after use with white spirit.

Storage

After use replace lid firmly and shake to ensure an airtight seal. Shelf life is indefinite if the container is kept sealed and stored in a dry area.

Specification Clause

LIQUID WATERPROOFER supplied by Adawall Construction Chemicals should be applied according to manufacturer's instructions.

Health and Safety

Care should be taken to avoid splashes entering eyes. Contact with skin should be avoided and hands washed thoroughly in the event of accidental contact. LIQUID WATERPROOFER should not be ingested. If splashes affect eyes, they should be bathed immediately with copious quantities of clean water and if discomfort persists medical attention should be sought without delay.

Full details are given on the separate Safety Data Sheet.